

CHEMICAL ANALYSIS	
Calcium Carbonate (CaCO ₃)	53.5
Magnesium Carbonate (MgCO ₃)	42.0
Total Carbonates	97.5
Calcium Oxide (CaO)	30.0
Magnesium Oxide (MgO)	20.0
Total Oxides	51.0
Elemental Calcium	21.4
Elemental Magnesium	12.1

SCREEN ANALYSIS	
U.S. Standard Sieve	% Through
20 Mesh	100
60 Mesh	95
100 Mesh	75-85
200 Mesh	50-60

BAKER'S RP - 40

- is an industrial limestone with a wide variety of uses as an extended or filler, acid neutralizer, separation media, or as a chemical additive.

